

CHAPAS FINAS A FRIO

Bitola MSG	Espessura		Peso	
	mm	pol.	KG/m ²	KG/pé ³
17	1,37	0,054	10,985	1,021
19	1,06	0,042	8,544	0,794
21	0,84	0,033	6,713	0,624
23	0,68	0,027	5,493	0,510
25	0,53	0,021	4,272	0,397
27	0,42	0,016	3,357	0,312
29	0,34	0,014	2,746	0,255

CHAPAS FINAS A QUENTE

Bitola MSG	Espessura		Peso
	mm	pol.	KG/m ²
7	4,55	0,179	36,618
9	3,80	0,150	30,515
11	3,04	0,120	24,412
13	2,28	0,090	18,309
15	1,71	0,067	13,732

CHAPAS GROSSAS

Pol.	Espessura		Peso	
	mm	pol.	KG/m ²	KG/pé ³
1/4	6,35	0,25	49,979	4,626
5/16	7,94	0,3125	62,246	5,783
11/32	8,73	0,34375	68,470	6,361
13/32	10,32	0,40625	80,920	7,518
15/32	11,91	0,46875	93,369	8,674
1/2	12,70	0,5	99,593	9,253
9/16	14,29	0,5625	112,043	10,409

5/8	15,88	0,625	124,492	11,566
21/32	16,67	0,65625	130,716	12,144
23/32	18,26	0,71875	143,166	13,301
25/32	19,84	0,78125	155,615	14,457
13/16	20,64	0,8125	161,839	15,035
7/8	22,23	0,875	174,288	16,192
15/16	23,81	0,9375	186,738	17,348
31/32	24,61	0,96875	192,962	17,927
1 1/16	26,9	1,0625	211,636	19,662
1 3/16	30,16	1,1875	236,534	21,975
1 1/4	31,75	1,25	248,984	23,131
1 3/8	34,93	1,375	273,882	25,444
1 1/2	38,10	1,5	298,780	27,758
1 5/8	41,28	1,625	323,679	30,071
1 7/8	47,63	1,875	373,475	34,697

CHAPAS GALVANIZADAS

Bitola GSG	Peso das Chapas	
	KG/m ²	KG/pé
13	19,072	1,773
15	14,495	1,348
17	11,748	1,092
19	9,307	0,865
21	7,476	0,695
23	6,256	0,582
25	5,035	0,468
27	4,120	0,383
29	3,509	0,326